

Reference: T2023150 - HADES

Determination of the abrasion resistance - Martindale

Date of ending the test 03-11-2020
Standard used ISO 12947-2 (2016)

Deviation from the standard -
Conditioning 20°C, relative humidity 65%
Apparatus Martindale Wear and Abrasion Tester
Pressure on test specimen 12 kPa
Abradant Standard wool fabric
Type of the felt Woven felt
Approximate g/m² 291
Number of test specimens 3

Test end point Flat - 2 yarns broken

Specimen	Number of cycles	Final result
#1	30 000	25 000
#2	30 000	25 000
#3	30 000	25 000
Minimum value	30 000	25 000