



Indetex nv
Rue du Mont Gallois 58
7700 MOUSCRON

Your notice of
03-03-2023

Your reference

Date
30-03-2023

Analysis Report 23.01248.01


Required tests :

IMO - 2010 FTP Code Annex 1 - Fire Test Procedures - Test for vertically supported textiles and films
Fire test procedures - Part 7

Sample id	Information given by the client	Date of receipt
T2305326	CORVO	03-03-2023

Petra Wittevrongel
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Reference: T2305326 - CORVO

IMO curtains

Information given by the client

Type of material	Curtain
Fabric	
Composition	100% Polyester FR
Structure	Plain
Number of threads - warp	31/cm
Number of threads - weft	44/cm
Yarn count - warp	75 den
Yarn count - weft	100 den
Thickness in mm	0.55
Weight g/m ²	250
Colour	-
Inherently FR treated	yes
Description of the coating	acrylic foam

Reference: T2305326 - CORVO

Fire Test Procedures - Test for vertically supported textiles and films

Date of ending the test 28-03-2023
Standard used IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 7
Deviation from the standard -
Conditioning Min 24 hours at 20°C and 65% RH
The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.
Information given by the client Face A ≠ face B
Dimension of the specimens 220 mm x 170 mm x < 1 mm
Weight (g/m²) 247
Flame application time (s) 5 - 15

Face A

Determination of the test conditions.

Length

	Surface		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	0	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	45	87	42	55
<u>Additional observations</u>				
Non-flaming debris	no	no	no	no
Damaged width (mm)	21	19	18	17

No sustained ignition: testing continued under conditions showing the greatest damaged length.

Width

	Surface		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	0	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	62	118	29	48
Additional observations				
Non-flaming debris	no	no	no	no
Damaged width (mm)	24	26	16	18

No sustained ignition: testing continued under conditions showing the greatest damaged length.

Worst testing conditions

Length Surface - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	87	80	81	107	87	88
Additional observations						
Non-flaming debris	no	no	no	no	no	
Damaged width (mm)	19	22	25	26	30	

Width Surface - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	118	100	93	102	104	103
<u>Additional observations</u>						
Non-flaming debris	no	no	no	no	no	
Damaged width (mm)	26	31	24	22	28	

Face B

Determination of the test conditions.

Length

	Surface		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	4	0	0	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	78	103	38	44
<u>Additional observations</u>				
Non-flaming debris	no	no	no	no
Damaged width (mm)	20	25	20	21

No sustained ignition: testing continued under conditions showing the greatest damaged length.

Width

	Surface		Edge	
Flame application time (s)	5	15	5	15
Afterflame time (s)	0	0	2	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	55	107	44	64
<u>Additional observations</u>				
Non-flaming debris	no	no	no	no
Damaged width (mm)	20	24	18	21

No sustained ignition: testing continued under conditions showing the greatest damaged length.

Worst testing conditions

Length Surface - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	103	87	116	104	92	100
<u>Additional observations</u>						
Non-flaming debris	no	no	no	no	no	
Damaged width (mm)	25	25	26	26	23	

Width Surface - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	107	79	98	78	85	89
Additional observations						
Non-flaming debris	no	no	no	no	no	
Damaged width (mm)	24	22	24	27	23	

Criteria for curtains and drapes

1. Afterflame time $\leq 5s$ for any specimen tested with face ignition.
2. No flame propagation to the edges for any specimen tested with face ignition..
3. No ignition of the cotton wool for any specimen.
4. Average char length ≤ 150 mm in any of the batches tested with face or edge ignition.
5. No occurrence of a surface flash more than 100 mm from the point of ignition.

Remark: If the test for length and/or width is carried out with edge ignition, the results obtained through the edge application are considered for the purposes of the criteria 1 and 2.

The fabric passes the proposed criteria for curtains and drapes.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.