



Indetex nv
Rue du Mont Gallois 58
7700 MOUSCRON

Your notice of
12-02-2024

Your reference

Date
04-03-2024

Analysis Report 24.00787.01

Required tests :

NF P92-507 (2004)

Sample id	Information given by the client	Date of receipt
T2403103	BIELLA	12-02-2024

Gina Créelle
Order responsible


This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Samples

T2403103
BIELLA





Reference: T2403103 - BIELLA

Classification of materials according to their reaction to fire - "Flame persistence test"

Date of ending the test 04-03-2024
Standard used NF P92-504 (1995)
Product standard NF P92-507 (2004)

Deviation from the standard -

Dimension of the specimens 460 mm x 230 mm x < 1 mm
Weight (g/m²) 277

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure

Conditioning 23°C, relative humidity 50%
Minimum 7 days or until constant mass is achieved

Each test has been carried out with a flame application time of 5s.

	Length		Width	
	Front	Back	Front	Back
#1	*	*	*	*
#2	*	*	*	*
#3	*	*	*	*
#4	*	*	*	*
#5	*	*	*	*
#6	*	*	*	*
#7	*	*	*	*
#8	*	*	*	*
#9	*	*	*	*
#10	*	*	*	*

Flaming debris no
Non-flaming debris no

*: afterflame time ≤ 2 s
> 2 s: afterflame time > 2 s and ≤ 5 s
> 5 s: afterflame time > 5 s

Provisional conclusion

The best possible classification is M1
A final classification can only be assigned after having carried out a complete series of tests.