



Indetex nv
Rue du Mont Gallois 58
7700 MOUSCRON

Your notice of
25-01-2023

Your reference

Date
07-02-2023

Analysis Report 23.00478.02

Required tests :

EN 13773 (2003)

Sample id	Information given by the client	Date of receipt
T2302095	RIVOLI	25-01-2023

Gina Créelle
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.




Reference: T2302095 - RIVOLI

Washing and drying

Date of ending the test	30-01-2023
Standard used	ISO 10528 (1995)
Deviation from the standard	-
Apparatus	Wascator FOM 71 (type A)
Used detergent	IEC detergent
Washing method and temperature	66- 30°
Drying method	A = Line dry (2021)
Number of washing cycles	4
Mass of the test specimens	1328 g

Sample generated: T2302095_01d



Reference: T2302095_01d - RIVOLI

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test 06-02-2023
 Standard used EN 1101 (1995) + A1 (2005)
 Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%
 Room 21°C, relative humidity 37%

Ignition Bottom edge


The test specimens have been washed 4 times instead of 12 times.

Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated

No ignition within 20 s



Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated
No ignition within 20 s

Reference: T2302095_01d - RIVOLI

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 07-02-2023
Standard used EN 13772 (2011)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have been washed 4 times instead of 12 times.

Length

	Face A	Face B	Face B	Face B
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	130	135	135	135
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face A	Face A
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	140	135	130	130
Flaming debris	no	no	no	no

Classification in accordance with EN 13773 Class 1