

Indetex nv Rue du Mont Gallois 58 7700 MOUSCRON

Your notice of 13-09-2024

Your reference

Date 23-10-2024

Analysis Report 24.04905.03

Required tests :

EN 13773 (2003)

Sample id	Information given by the client	Date of receipt
T2418006	VICENZE	13-09-2024

néelle

Gina Créelle Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel. The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples. In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



CENTEXBEL • textile competence centre • www.centexbel.be • www.vkc.be

GENT • Technologiepark 70 • BE-9052 Zwijnaarde, Belgium • phone +32 9 220 41 51 • fax +32 9 220 49 55 • gent@centexbel.be GRÂCE-HOLLOGNE • Rue du Travail 5 • BE-4460 Grâce-Hollogne, Belgium • phone +32 4 296 82 00 • g-h@centexbel.be KORTRIJK • Etienne Sabbelaan 49 • BE-8500 Kortrijk, Belgium • phone +32 56 29 27 00 • fax +32 56 29 27 01 • info@vkc.be VAT BE 0459.218.289 • IBAN BE44 2100 4729 6545 • BIC GEBABEBB



Analysis Report 24.04905.03 Date 23-10-2024 Page 2/6

Samples

T2418006 VICENZE



in

f



Analysis Report 24.04905.03 Date 23-10-2024 Page 3/6

Reference: T2418006 - VICENZE

Washing and drying

Date of ending the test Standard used	01-10-2024 ISO 6330 (2000) + A1 (2008), ISO 6330 (2012)
Deviation from the standard Conditioning Apparatus Used detergent Washing method and temperature Drying method Number of washing cycles	20°C, relative humidity 65% Wascator FOM 71 (type A) ECE detergent (Type 3) 8A- 30°C (2000) A = Line dry 3
Mass of the test specimens Mass of the ballast	1866g The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2418006_01d

in f



Reference: T2418006_01d - VICENZE

<u>Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the</u> <u>ignitability of vertically oriented specimens.</u>

Date of ending the test Standard used Product standard	17-10-2024 EN 1101 (1995) + A1 (2005) EN 13773 (2003)
Deviation from the standard	-
Conditioning Testing atmosphere	20°C, relative humidity 65% 22°C, relative humidity 68%
Dimension of the specimens	200 mm x 80 mm
Ignition	Bottom edge

The test specimens have been washed 3 times instead of 1 time.

Length

Cases of	Cases of
ignition	non-ignition
0	1
0	1
0	1
0	1
0	1
0	1
0	1
0	5
	Cases of ignition 0 0 0 0 0 0 0 0 0 0 0

The mean of the recorded times at which ignition was observed is calculated No ignition within 20 s

f



Width		
Flame application	Cases of	Cases of
time (s)	ignition	non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated No ignition within 20 s

Minimum ignition time

No ignition within 20 s

f



Reference: T2418006_01d - VICENZE

<u>Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of</u> <u>flame spread of vertically oriented specimens with large ignition source.</u>

Date of ending the test	22-10-2024
Standard used	EN 13772 (2011)
Product standard	EN 13773 (2003)

Deviation from the standard

Conditi	oning
Conun	oning

20°C, relative humidity 65%

The test specimens have been washed 3 times instead of 12 times.

Length

	Front	Back	Front	Front
Severance1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	160	145	150	135
Flaming debris	no	no	no	no

Width

	Front	Back	Front	Front
Severance1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	155	140	145	150
Flaming debris	no	no	no	no

Classification in accordance with EN 13773

Class 1