



**Indetex nv**  
**Rue du Mont Gallois 58**  
**7700 MOUSCRON**

**Your notice of**  
 10-03-2025

**Your reference**

**Date**  
 11-04-2025

## Analysis Report 25.01301.01

Required tests :


**EN 13773 (2003)**

Sample id	Information given by the client	Date of receipt
T2505138	ALVIANO	10-03-2025



Gina Créelle  
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.  
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.  
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



## Samples

T2505138  
ALVIANO





**Reference: T2505138 - ALVIANO**

**Washing and drying**

Date of ending the test	13-03-2025
Standard used	ISO 6330 (2000) + A1 (2008), ISO 6330 (2012)
Deviation from the standard	-
Conditioning	20°C, relative humidity 65%
Apparatus	Wascator FOM 71 (type A)
Used detergent	ECE detergent (Type 3)
Washing method and temperature	3A- 60°C (2000)
Drying method	A = Line dry (2000)
Number of washing cycles	3
Mass of the test specimens	1454 g
Mass of the ballast	The washing machine is filled with ballast to achieve 2 kg in total
Remark	Washing always occurs with a ballast type III 100% PES regardless of the composition of the fabric.

Sample generated: T2505138\_01d



**Reference: T2505138\_01d - ALVIANO**

**Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.**

Date of ending the test 09-04-2025  
Standard used EN 1101 (1995) + A1 (2005)  
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%  
Testing atmosphere 21°C, relative humidity 36%

Dimension of the specimens 200 mm x 80 mm

Ignition Bottom edge

The test specimens have been washed 3 times instead of 1 time.\*

\*Based on information given by the client.

**Length**

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
No ignition within 20 s



### Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	1
5	0	1
10	0	1
15	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated  
 No ignition within 20 s

Minimum ignition time

No ignition within 20 s



**Reference:** T2505138\_01d - ALVIANO

**Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.**

Date of ending the test 11-04-2025  
Standard used EN 13772 (2011)  
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have been washed 3 times instead of 12 times.\*

\*Based on information given by the client.

**Length**

	Front	Back	Front	Front
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	150	150	140	150
Flaming debris	no	no	no	no

**Width**

	Front	Back	Back	Back
Severance 1 <sup>st</sup> thread	no	no	no	no
Severance 2 <sup>nd</sup> thread	no	no	no	no
Severance 3 <sup>rd</sup> thread	no	no	no	no
Time to sever 3 <sup>rd</sup> thread (s)	/	/	/	/
Destroyed length (mm)	140	145	155	140
Flaming debris	no	no	no	no



**Reference: T2505138 - ALVIANO**

**Classification of curtains and drapes according to EN 13773**

Product standard EN 13773 (2003)

Provisional classification\* in Class 1  
accordance with EN 13773:

Classification based on\*:  
EN 1101 after 3 washes.  
EN 13772 after 3 washes.

A final classification can only be assigned after having carried out:  
EN 1101 after 1 wash.  
EN 13772 on original material.  
EN 13772 after 12 washes.