



Indetex nv
Rue du Mont Gallois 58
7700 MOUSCRON

Your notice of
 14-07-2025

Your reference

Date
 16-07-2025

Analysis Report 25.03869.01

Required tests :

EN 13773 (2003)

Sample id	Information given by the client	Date of receipt
T2514167	DONNINI	14-07-2025



Gina Créelle
 Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
 The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
 In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.



Samples

T2514167
DONNINI





Reference: T2514167 - DONNINI

Textiles – Burning behaviour – Curtains and drapes - Textile fabrics - Determination of the ignitability of vertically oriented specimens.

Date of ending the test	16-07-2025
Standard used	EN 1101 (1995) + A1 (2005)
Product standard	EN 13773 (2003)

Deviation from the standard	-
-----------------------------	---

Conditioning	20°C, relative humidity 65%
Testing atmosphere	25°C, relative humidity 47%

Dimension of the specimens	200 mm x 80 mm
----------------------------	----------------

Ignition	Bottom edge
----------	-------------

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.*

*Based on information given by the client.




Length

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	1
3	0	1
4	0	2
5	1	1
6	0	2
7	1	1
8	0	1
9	0	1
10	0	1
11	0	1
12	0	1
13	0	1
14	0	1
15	0	1
16	0	1
17	0	1
18	0	1
19	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated

The test requires at least five instances of ignition and five instances of non-ignition.

Because less than 5 instances of ignition have been measured, and taking into account §12 of ISO 6940, a 'non-ignition' for this test is recorded



Width

Flame application time (s)	Cases of ignition	Cases of non-ignition
1	0	1
2	0	2
3	1	2
4	1	1
5	0	1
6	0	1
7	0	1
8	0	1
9	0	1
10	0	1
11	0	1
12	0	1
13	0	1
14	0	1
15	0	1
16	0	1
17	0	1
18	0	1
19	0	1
20	0	5

The mean of the recorded times at which ignition was observed is calculated

The test requires at least five instances of ignition and five instances of non-ignition.

Because less than 5 instances of ignition have been measured, and taking into account §12 of ISO 6940, a 'non-ignition' for this test is recorded

Minimum ignition time

The test requires at least five instances of ignition and five instances of non-ignition.

Because less than 5 instances of ignition have been measured, and taking into account §12 of ISO 6940, a 'non-ignition' for this test is recorded

Reference: T2514167 - DONNINI

Textiles and textile products – Burning behaviour – Curtains and drapes. Measurement of flame spread of vertically oriented specimens with large ignition source.

Date of ending the test 16-07-2025
Standard used EN 13772 (2011)
Product standard EN 13773 (2003)

Deviation from the standard -

Conditioning 20°C, relative humidity 65%

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Length

	Face A	Face B	Face B	Face B
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	125	130	125	130
Flaming debris	no	no	no	no

Width

	Face A	Face B	Face A	Face A
Severance 1 st thread	no	no	no	no
Severance 2 nd thread	no	no	no	no
Severance 3 rd thread	no	no	no	no
Time to sever 3 rd thread (s)	/	/	/	/
Destroyed length (mm)	125	125	130	140
Flaming debris	no	no	no	no



Reference: T2514167 - DONNINI

Classification of curtains and drapes according to EN 13773

Product standard EN 13773 (2003)

Classification in accordance with EN 13773 Class 1