INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Indetex nv
Rue du Mont Gallois 58
7700 MOUSCRON

Your notice of	**Your reference**	**Date**
15-09-2026		19-11-2026

Analysis Report 26.04827.01

Required tests :
IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 7 **Fire Test Procedures - Test for vertically supported textiles and films**

Sample id	Information given by the client	Date of receipt
T2619446	DONNINI	15-09-2026

Petra Wittevrongel
Order responsible

This report may be reproduced, as long as it is presented in its entire form, without written permission of Centexbel.
The results of the analysis cover the received samples. Centexbel is not responsible for the representativeness of the samples.
In assessing compliance with the specifications, we did not take into account the uncertainty on the test results.

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Reference: **T2619446 - DONNINI**

IMO curtains

Information given by the client

Type of material	Curtain

Fabric

Composition	100% PES
Structure	Weave
Number of threads - warp	10/cm
Number of threads - weft	10/cm
Yarn count - warp	-
Yarn count - weft	-
Thickness in mm	0.20
Weight g/m²	210
Colour	-
Inherently FR treated	yes
Description of the coating	Not applicable

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Reference: **T2619446 - DONNINI**

Fire Test Procedures - Test for vertically supported textiles and films

Date of ending the test	13-11-2026
Standard used	IMO - 2010 FTP Code Annex 1 - Fire test procedures - Part 7
Deviation from the standard	-
Conditioning	Min 24 hours at 20°C and 65% RH

The test specimens have not been cleaned nor submitted to an accelerated ageing procedure.

Information given by the client	Front ≠ back
Dimension of the specimens	220 mm x 170 mm x 1 mm
Weight (g/m²)	201
Flame application time (s)	5 - 15

Front

Determination of the test conditions.

Length

	Surface		Edge	
Flame application time (s)	**5**	**15**	**5**	**15**
Afterflame time (s)	0	0	0	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	30	35	43	50
Additional observations				
Non-flaming debris	no	no	no	no
Damaged width (mm)	16	16	17	28

No sustained ignition: testing continued under conditions showing the greatest damaged length.

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Width

	Surface		Edge	
Flame application time (s)	**5**	**15**	**5**	**15**
Afterflame time (s)	1	0	0	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	30	38	46	63
Additional observations				
Non-flaming debris	no	no	no	no
Damaged width (mm)	16	18	20	22

No sustained ignition: testing continued under conditions showing the greatest damaged length.

Worst testing conditions

Length Edge - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	50	66	68	53	45	56
Additional observations						
Non-flaming debris	no	no	no	no	no	
Damaged width (mm)	28	20	20	15	17	

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Width Edge - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	63	53	49	65	57	57
Additional observations						
Non-flaming debris	no	no	yes	no	no	
Damaged width (mm)	22	18	19	20	19	

Back

Determination of the test conditions.

Length

	Surface		Edge	
Flame application time (s)	**5**	**15**	**5**	**15**
Afterflame time (s)	0	0	0	0
Surface flash	no	no	no	no
Edge reached	no	no	no	no
Ignition cotton wool	no	no	no	no
Maximum damaged length (mm)	25	37	44	59
Additional observations				
Non-flaming debris	no	no	no	no
Damaged width (mm)	18	18	20	19

No sustained ignition: testing continued under conditions showing the greatest damaged length.

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Width

	Surface		Edge	
Flame application time (s)	**5**	**15**	**5**	**15**
Afterflame time (s)	10			
Surface flash	no			
Edge reached	no			
Ignition cotton wool	no			
Maximum damaged length (mm)	64			
Additional observations				
Non-flaming debris	no			
Damaged width (mm)	27			

Worst testing conditions

Length Edge - flame application time 15 s

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	59	63	57	60	64	61
Additional observations						
Non-flaming debris	no	no	no	no	no	
Damaged width (mm)	19	21	19	22	18	

INRICHTING ERKEND BIJ TOEPASSING VAN DE BESLUITWET VAN 30 JANUARI 1947 / ETABLISSEMENT RECONNU PAR APPLICATION DE L'ARRÊTE-LOI DU 30 JANVIER 1947

Width Surface - flame application time 5 s

	1	2	3	4	5	Average
Afterflame time (s)	10	0	5	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	64	29	41	28	28	38
Additional observations						
Non-flaming debris	no	no	no	no	no	
Damaged width (mm)	27	16	27	15	15	

Additional tests

	1	2	3	4	5	Average
Afterflame time (s)	0	0	0	0	0	
Surface flash	no	no	no	no	no	
Edge reached	no	no	no	no	no	
Ignition cotton wool	no	no	no	no	no	
Maximum damaged length (mm)	31	26	26	25	33	28
Additional observations						
Non-flaming debris	no	no	no	no	no	
Damaged width (mm)	17	15	15	16	19	

Criteria for curtains and drapes

1. Afterflame time ≤ 5s for any specimen tested with face ignition.
2. No flame propagation to the edges for any specimen tested with face ignition..
3. No ignition of the cotton wool for any specimen.
4. Average char length ≤ 150 mm in any of the batches tested with face or edge ignition.
5. No occurance of a surface flash more than 100 mm from the point of ignition.

Remark: If the test for length and/or width is carried out with edge ignition, the results obtained through the edge application are considered for the purposes of the criteria 1 and 2.

The fabric passes the proposed criteria for curtains and drapes.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test: they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.